

VULCANO PU HDS 15 ESTERE VC



- 应用于重磨损材料，聚酯型聚氨酯材质的耐磨型软管

颜色:

- 半透明

温度:

- -40°C + 90°C (短时间可耐 +125° C)

应用:

- 适用于磨损性物，如：颗粒、碎料的传输和抽吸。在塑料行业、PCB行业中可用于塑料粒子和碎料的高速传输。在印刷行业以及工业真空清洁领域也得到广泛应用。

技术特性:

- 聚酯型聚氨酯材质，包塑镀铜钢丝螺旋加强。
- 非螺旋处壁厚恒定为1.5毫米
- 内壁平滑，保证物料流动顺畅
- 机械特性及真空性能卓越，厚实但柔韧，耐磨，耐矿物油和多数化学物质。
- 不含卤素
- 不含邻苯二甲酸盐
- 软管两端螺旋钢丝接地可排静电。

- Heavy abrasion, Ester-based Polyurethane, abrasion resistant

Colour:

- translucent.

Temperature range:

- -40 C + 90 C (intermittent up to +125 C).

Applications:

- Ideal for suction and delivery many type of highly abrasive media in a wide range of industries: such as granules, abrasive powders, pellets. Suitable to be used for conveying systems in plastic sector, woodworking, glass and ceramic industries, construction and material handling, vacuum excavation, shot blast.

Technical features:

- Ester-based Polyurethane reinforced with PU coated high adhesion coppered steel spiral.
- Constant wall thickness 1.5mm under the spiral.
- Smooth inside to ensure optimization of flow.
- Excellent mechanical properties and vacuum performances: strong but still flexible, resistance to abrasion, mineral oils, most chemicals.
- Halogens free.
- Phthalates free.
- The hose becomes electrically-conductive by grounding the spiral (both ends).



VULCANO PU HDS 15 ESTERE VC

代码 Part number	内径Φ Inside Φ (mm)	最小壁厚 Min wall th. (mm)	重量 Weight (g/m)	弯曲半径 Bending radius (mm)	耐负压 Vacuum (mH20)	每卷长度 Roll length (m)	体积 Volume (m3)	桥式卡箍 W2 Double bridge W2
VC0102000000	20*	1.5	245	25	9.5	20	0.040	-
VC0102500000	25*	1.5	305	30	9.5	20	0.050	-
VC0103000000	30*	1.5	440	35	9.5	20	0.060	-
VC0103200000	32*	1.5	465	35	9.5	20	0.060	-
VC0103500000	35*	1.5	500	40	9.5	20	0.060	-
VC0103800000	38	1.5	535	40	9.5	20	0.090	-
VC0104000000	40	1.5	560	50	9.5	20	0.090	-
VC0104500000	45*	1.5	620	50	9.0	20	0.100	-
VC0105000000	50	1.5	685	60	9.0	20	0.110	-
VC0105100000	51	1.5	695	60	9.0	20	0.120	-
VC0106000000	60	1.5	810	70	8.5	20	0.130	-
VC0106300000	63	1.5	845	70	8.0	20	0.140	-
VC0106500000	65*	1.5	870	70	7.5	20	0.190	-
VC0107000000	70	1.5	1005	80	7.5	20	0.200	-
VC0107600000	76	1.5	1090	90	7.0	20	0.250	-
VC0108000000	80	1.5	1140	90	6.0	20	0.260	F2 W2 076.0 090.0
VC0109000000	90	1.5	1275	100	5.0	20	0.290	F2 W2 076.0 090.0
VC0110000000	100*	1.5	1410	120	4.0	15	0.320	F2 W2 100.0 127.0
VC0110200000	102	1.5	1435	120	3.5	15	0.320	F2 W2 100.0 127.0
VC0111000000	110*	1.5	1545	130	3.2	15	0.350	F2 W2 100.0 127.0
VC0111500000	115*	1.5	1610	135	3.0	15	0.360	F2 W2 100.0 127.0
VC0112000000	120	1.5	1675	140	3.0	15	0.370	F2 W2 100.0 127.0
VC0112700000	127	1.5	2075	150	2.9	15	0.400	F2 W2 100.0 127.0
VC0113000000	130*	1.5	2120	150	2.6	15	0.610	F2 W2 130.0 190.0
VC0114000000	140	1.5	2275	160	2.4	15	0.650	F2 W2 130.0 190.0
VC0115000000	150*	1.5	2435	170	2.0	15	0.690	F2 W2 130.0 190.0
VC0115200000	152	1.5	2465	170	2.0	15	0.700	F2 W2 130.0 190.0
VC0116000000	160	1.5	2590	180	1.8	15	0.740	F2 W2 130.0 190.0
VC0117500000	175*	1.5	2705	200	1.5	15	0.950	F2 W2 130.0 190.0
VC0118000000	180	1.5	2780	210	1.5	15	0.980	F2 W2 130.0 190.0
VC0120000000	200*	1.5	3080	230	1.2	15	1080.000	F2 W2 200.0 230.0
VC0120300000	203	1.5	3125	230	1.2	15	1100.000	F2 W2 200.0 230.0
VC0122800000	228*	1.5	3500	260	1.0	10	1230.000	F2 W2 200.0 230.0
VC0125000000	250*	1.5	3830	290	0.8	10	1340.000	F2 W2 250.0 330.0
VC0125400000	254	1.5	3890	290	0.8	10	1360.000	F2 W2 250.0 330.0
VC0127900000	279*	1.5	4265	320	0.7	10	1490.000	F2 W2 250.0 330.0
VC0130500000	305	1.5	5680	350	0.7			F2 W2 250.0 330.0
VC0132000000	320*	1.5	5955	ND	0.7	A richiesta (max 10m) pz dritti/On request (max 10m) straight pieces		F2 W2 350.0 410.0
VC0135000000	350*	1.5	6500	ND	0.7			F2 W2 350.0 410.0
VC0140000000	400*	1.5	7415	ND	0.7			F2 W2 350.0 410.0
VC0140600000	406*	1.5	7525	ND	0.7			F2 W2 350.0 410.0
VC0150000000	500*	1.5	9240	600	0.2	5	1306	

* Available on request, contact our sales office for more info and quantities

* 如有需要, 请我们的销售办公室联系以获取更多信息和数量

The technical data here reported were measured at 23° c with 50% humidity

技术参数均在23°C 50%湿度下测量

